



TURBO-LINER 12

Two-Component Polyurethane Primer

DESCRIPTION

Turbo-Liner 12 is a two component, 100% solids, liquid applied, urea polyurethane primer.

FEATURES

- ❖ Low Odor
- ❖ Solvent Free
- ❖ 100% Solids
- ❖ Quick Drying

TYPICAL USES

- ❖ Metal
- ❖ Glass Reinforced Plastics
- ❖ Polyurethane Elastomeric Surfaces

COLOR

Part-A: Black, Part-B: White

PACKAGING

3 gallon kit:

One - 1 gallon (3.78 liter) can of Part-A Black Liquid, net 1 gallon and One 3.5 gallon pail of Part-B White Liquid, net 2 gallons (7.56 liter).

15 gallon kit:

One - 5 gallon (18.9 liter) pail of Part-A Black Liquid, containing 5 gallons. Two - 5 gallon (18.9 liter) pails of Part-B White Liquid, each containing 5 gallons.

COVERAGE

Approximate coverage per gallon is 300 per sq.ft

SURFACE PREPARATION

Remove all contaminant, oil and grease from substrate.

MIXING

Turbo-Liner 12 may not be diluted under any circumstance. The volume mixing ratio: 1 part Part-A Black Liquid to 2 parts Part-B White Liquid. Turbo-Liner 12 Part-B should be thoroughly mixed prior to combining to ensure a homogeneous material. The combined components should be thoroughly mixed using a mechanical mixer at slow speed or for at least 5 minutes if mixed by hand.

APPLICATION

Turbo-Liner 12 should be applied at the rate of 1 gallon (mixture of Part-A & Part-B)/400 sq. ft. (0.102 liters/m²). It can be applied using an airless sprayer, brush, or phenolic resin core roller.

Allow Turbo-Liner 12 to become nearly tack free before applying the coating. Recommended surface temperature should be greater than 50°F (10°C). If Turbo-Liner 12 is allowed to dry completely, re-prime the surface before proceeding.

Turbo-Liner 12 is very sensitive to heat and moisture. Higher temperatures and/or high humidity will significantly accelerate the cure time and pot life. Use caution in batch sizes and thickness of application. Low temperature and/or low humidity extend the cure time.

STORAGE

Turbo-Liner 12 has a shelf life of one (1) year from date of manufacture in original, factory sealed containers.

Part-A and Part-B must be stored above 60°F (15°C).

Avoid freezing temperatures.

Store containers on wooden pallets to avoid direct contact with the ground.

TECHNICAL DATA

Coverage Rate	1 gal/300 sq. ft. 1.135 l/m ²
Mixing Ratio by Volume	1A : 2B
Dry Film Thickness per Coat	5 ± 1 mils 127 ± 25 mic
Pot Life at 75°F (24°C), 50%RH	20-30 minutes
Hardness, ASTM D-2240	70 ± 5 D
Specific Gravity,	
Part-A	1.23
Part-B	1.65
Total Solids, Weight, ASTM D-2369	100%
Total Solids, Volume, ASTM D-2697	100%
Viscosity at 75°F (24°C),	
Part-A	200 ± 100 cps
Part-B	4000 ± 500 cps
Volatile Organic Components,	
ASTM D-2369-81	0 lbs/gal 0 gm/liter



TURBO-LINER 12

Two-Component Polyurethane Primer

LIMITATIONS

Not UV stable.

Cannot withstand direct wear or abrasion.

Containers that have been opened must be used as soon as possible.

Turbo-Liner 12 is difficult to clean up after it has cured.

Mix no more material than can be used within 20 minutes.

WARNING

This product contains Isocyanates.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Turbo Products representative or visit our website for current technical data and instructions.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Turbo Products makes no claim that these tests or any other tests, accurately represent all environments.