



**TURBO LINER
PRODUCTS INC.
1 W. CAMERON
KELLOGG, ID 83837
877-678-8726**

POLYGLAZE AR *Aromatic Urethane Polyurea Topcoat*

DESCRIPTION

Polyglaze AR is an aromatic, two component, liquid applied, moisture cured, urethane polyurea coating.

FEATURES

- ❖ Good Weatherability

TYPICAL USES

- ❖ Concrete
- ❖ Pedestrian Traffic
- ❖ Resealing Existing Urethane Surfaces
- ❖ Metal, Rubber, Wood, or Masonry Surfaces
- ❖ Plywood
- ❖ Vehicular Traffic

COLORS

Stone Grey, Tan

Custom colors are also available. Minimum order of 300 gallons (1136 liters). See color chart for special provisions.

PACKAGING

1 gallon (3.78 liter) can with vial of catalyst
5 gallon (19 liter) pail with 2 pint (0.24 liter) can of catalyst
55 gallon drums, net fill 50 gallons (189 liters) with 1 quart (0.95 liter) can of catalyst

MIXING

Before application, mix Polyglaze AR using a mechanical mixer (Jiffy Mixer) at slow speeds or by hand for at least 5 minutes. Add Polyglaze AR Catalyst and continue mixing until a homogeneous mixture and color is obtained. Boxing of the material is recommended. Use caution not to whip too much air into the material as this may result in pinhole blisters or shortened potlife.

APPLICATION

For best results use a squeegee. Airless sprayer or phenolic resin core roller may be used but extra care should be taken not to cause air bubbles.

Apply Polyglaze AR evenly over the entire deck. Application should be continuous to ensure a smooth and level coat with no lines or streaks to disfigure the deck.

Polyglaze AR may require more than one coat depending on the job specifications and requirements. When estimating material requirements, coverage rates tend to increase for subsequent coats of material. To obtain proper adhesion between coats it is imperative that recoating be done within 48 hours.

When Polyglaze AR is used as a seal coat only, the surface must be clean, dry and primed with Polyprime 21 to achieve proper adhesion to the surface.

TECHNICAL DATA

Coverage Rate	See Guide Specifications
Dry Film Thickness, exclusive of aggregate, Per coat @ 1 gal/100 sq. ft.	11 ± 2 mils 280 ± 50 mic
Hardness, ASTM D-2240	90 ± 5 Shore A
Tear Resistance, Die C, ASTM D-624	310 ± 30 pli 51.00 ± 5 kN/m
Tensile Strength, ASTM D-412	4200 ± 400 psi 18.97 ± 2 MPa
Ultimate Elongation, ASTM D-412	500 ± 50%
Specific Gravity	1.17
Total Solids by Weight, ASTM D-2369	80.1%
Total Solids by Volume, ASTM D-2697	71.8%
Viscosity at 75°F (24°C)	1000 ± 500 cps
Volatile Organic Compounds, ASTM D-2369-81	2.08 lb/gal 248 gm/liter

CURING

At 70°F (21°C) and 50% relative humidity allow each coat to cure a minimum of 16 and a maximum of 48 hours between each coat. If more than 48 hours passes between coats, re-prime the surface with Polyprime 21 or 2180 before proceeding.

Allow 24 hours before permitting light pedestrian traffic and at least 72 hours before permitting heavy pedestrian or auto traffic on the finished surface.

Uncured Polyglaze AR is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application.

Low temperature and/or low humidity extend the cure time. To accelerate cure Polyglaze Hardener may be used.

EQUIPMENT CLEANUP

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

STORAGE

Polyglaze AR has a shelf life of six (6) months from date of manufacture in original, factory sealed containers.

LIMITATIONS

Surfaces must be dry, clean and free of foreign matter.

Surface may be slippery when wet.

Will fade, chalk and discolor over time.

Containers that have been opened must be used as soon as possible.

Do not dilute under any circumstance.

WARNING

This product contains Isocyanates and Solvent.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Turbo Products representative or visit our website for current technical data and instructions.

LIMITED WARRANTY

Turbo Products warrants its products to be free of manufacturing defects and that they will meet Turbo Products current published physical properties. Turbo Products warrants that its products, when properly installed by a state licensed waterproofing contractor according to Turbo Products guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of one (1) year. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. There are no other warranties by Turbo Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Turbo Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Turbo Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Turbo Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Turbo Products makes no claim that these tests or any other tests, accurately represent all environments.