

Chemical Loading Spill Containment

SCHLUMBERGER - Longview, Texas - 10-26-2001

By:
A.J. Wiseman



System:

Surface Prep: Sandblast—Black Beauty 12/40

Primer: Sherwin Williams—Dura-Plate 235

Top Coat: Polyurea Coating Systems—PCS-325 FS

Contractor:

M & M Contractors & Industrial Coatings
P. O. Box 287
Kilgore, TX 75663
Dale McElyra

Fast Set Coatings
900 Sagebrush Drive
Austin, TX 78758
Kurt DeRuiter

Coating Description:

The steel loading rack and stairs were blasted with Black Beauty 12/40 grit to a 3.5 mil profile, primed with 1.0 to 1.5 mil Dura-Plate 235 and top coated with 60 mils of PCS-325 FS.

The concrete containment area was blasted with Black Beauty 12/40 grit to remove old coating, primed with 2.0 mils Dura-Plate 235 and top coated with 80 mils of PCS-325 FS.